



## Product Data Sheet

### 79- Line

### Two Pack Epoxy Floor Paint

- ✓ Good Abrasion Resistance
- ✓ Good Chemical Resistance
- ✓ Fast Drying
- ✓ Easy to use

<b>Product &amp; Ancillaries</b>	79- Line R9 Thinner
<b>Suitable Substrates &amp; Preparation</b>	<p>Concrete should be clean dry and free from oil, grease, etc. The surface should have a coarse surface profile. Smooth, hard concrete (i.e.; 'powder-floated') should be abrasive, blasted or abraded to give a 'key' for the coating.</p> <p>Previously painted floors: Existing paint must be sound with good adhesion. Thoroughly clean with detergent water, rinse and dry off. We would recommend carrying out a small trial area to ensure compatibility with existing paint.</p> <p>New Concrete: Ensure concrete is fully cured. Apply sealer coat using 2S floor paint tinned 30% with Thinner R9.</p>
<b>Thinning/Mixing Ratio</b>	2.5 Base : 1 Activator
<b>Spraying Viscosity</b>	If Required
<b>Application Equipment</b>	May be applied by brush, roller or conventional spray. Thoroughly mix base component then add activator and continue to stir until homogeneous.
<b>Pot Life</b>	8 Hours once opened.
<b>Approved Thickness</b>	As Required

<b>Volume Solids</b>	55%
<b>Overcoatable with</b>	Overnight with 3 days (after 3 days lightly abrade and solvent wipe before over coating. (Will vary with temperature, air movement, etc.)
<b>Drying times</b>	Touch Dry: 2 Hours. Film Dry: 6 Hours.
<b>Coverage</b>	Typically 8M <sup>2</sup> per litre depending on film thickness applied and surface profile etc.
<b>Colours</b>	Limited colour range ex-stock, contact us for colour card.
<b>Gloss Level</b>	Glossy
<b>Properties</b>	

**Please refer to the Material Safety Data Sheet before using this product.**

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is to the best of the manufacturer's knowledge and belief accurate and reliable as of the date indicated. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability and completeness of such information for their own particular use. Therefore, Colour Dynamics Limited do not accept any liability whatsoever arising from the performance of the product or for loss of damage (other than death or personal injury resulting from our negligence) arising out of the use of this product.