



Product	PD911278G METALLIC BLACK GREY POLYESTER GLOSS
Curing	10 MINS @ 180C Metal Temperature
Brilliance	Visual Only
Approvals	

PRODUCT DESCRIPTION

The Metallic range has been formulated to provide a range of aesthetically appealing metallic effects. In general, these coatings are not suitable for severe environments. Both bonded and blended products are available as are certain grades suited to exterior use. Our attention to particle size control and formulation ensures optimum transfer efficiency.

Care must be taken when handling coated components; for some products direct skin contact and abrasive packaging should be avoided as much as possible. A protective coating with a clear lacquer may be required for external use or when in a harsher environment to maintain the metallic effect. Some metallic pigments are readily degraded by regular or continuous exposure to water or humidity. We recommend that you also carry out your own testing where required to ensure full suitability prior to use of a specific product. If in doubt please discuss the final application with your Sherwin-Williams representative.

Storage Life:

Store in dry, cool conditions, preferably below 25°C. Shelf life under these conditions will be approx 12 months. For full information on handling this product type, refer to individual Safety Data Sheet and the 'Code of Safe Practice' issued by the British Coatings Federation.

CHARACTERISTICS

Spec. Gravity (kg/l): 1,2 – 1,8
(depending on colour, gloss and other properties)

Theoretical Coverage (m²/kg @60µ): 9-14
(100% utilisation assumed) depending on colour and gloss

Recommended film thickness:
Recommended 50-75 microns for most applications, depending on type.

Colour:
Wide range available

Gloss:
Gloss levels are described visually, as true measurement is not feasible

Heat Stability
Dependent on type. Heat resistant versions of these products can be formulated.

APPLICATION

Sherwin-Williams' metallic powders are suitable for use with electrostatic powder spraying equipment. The powder is sprayed electrostatically onto earthed metallic substrates and an even layer of powder is deposited.

When subjected to the correct temperature, the powder melts and flows to form a continuous film which is then cured. The same batch of powder should be used for each job and application conditions should be held constant. Spray from a well-mixed fluidised bed is preferable to direct box feed.

Curing Cycle
180°C/10 mins. Object temperature, typically, but refer to product data for details.

SUBSTRATE PREPARATION

The Sherwin-Williams' metallic powders adhere to most metals and do not require primers. Articles to be coated must be free from rust, grease, oil and mill scale.

Solvent vapor degreasing is usually adequate for interior applications however, in order to improve corrosion resistance, the use of iron phosphate or zinc phosphate is strongly recommended.

Aluminum should be pre-treated using a chromate conversion system prior to powder coating. Zinc based diecastings and Zintec should also be pre-treated. Our technical service department will be pleased to offer further advice on this subject if required.

PERFORMANCE DATA

Mandrel bend:

Pass 13mm
BS3900 E1

Adhesion:

No detachment
BS3900 E6

Impact resistance:

Pass 60 in/lb
ASTM D2794: 1969 (2.5Nm)

Scratch Test

Pass 2kg to substrate
BS3900 E2

NB. Substrate used in obtaining performance data was 0.8mm mild steel pre-treated using a medium weight zinc phosphate.

CAUTION

FOR INDUSTRIAL SHOP APPLICATION

Thoroughly review product label and Safety Data Sheet (SDS) prior to using this product.

A Safety Data Sheet is available from your local Sherwin-Williams facility or distributor

Note: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the user obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in user handling and methods of application which are not known or under our control, The Sherwin-Williams Company cannot make any warranties as to the end result.

APPLICATION GUIDELINES FOR METALLIC POWDER COATINGS

Introduction

Demand for metallic coating powders has increased significantly to the point where many users consider them to be the same as conventional coating powders. The user requires them to be readily available in their preferred color or effect and they are expected to apply in exactly the same way as any other non-metallic coating powders. With the current range of available colors and effects increasing, a wide variety of products have evolved all with differing types and levels of special effect pigments and as a result all can have different application properties. The result is that many metallic coating powders can be difficult to apply, showing poor quality of finish and inconsistent appearance if application conditions are not monitored and controlled.

To help get the result we can offer the advice below on how to select and apply our metallic coating powders.

Which product do I use?

Sherwin-Williams UK has three types of metallics available, Blended, Bonded and Hammer Finish. This document deals only with Blended and Bonded coating powders. The Hammer Finish is manufactured using different technology to the other two types of products and does not have the same application issues.

Blended metallics are simply dry-blends of a powder base with a special effect pigment. They are not recommended for reclaim systems and are best sprayed to waste! The special effect pigment can be

Rev. date: 01/03/2021

easily separated from the powder during application and recovery. This can result in reduced metallic effect second time round the system. Blended coating powders are recommended only when a small quantity is required and if application equipment can apply metallic powder without difficulty.

Sherwin-Williams UK Bonded metallics are put through a further specialized process that physically "bonds" the special effect pigment to the surface of the powder particle. This reduces separation of the special effect pigment from the powder allowing powder to be reclaimed more successfully, although this must be controlled, and we would not recommend exceeding 25% reclaim in virgin powder. Bonding also reduces the amount of "free" special effect pigment in the powder that can cause loss of electrostatic charge and spitting of metallic pigment.

The final use of the coated article should also be taken into account when selecting a metallic powder. Not all metallic effects are suitable for exterior use and some may require a clear lacquer topcoat to protect the metallic pigment from the weathering effects of the environment. Some metallic coatings may also finger mark more than others.

We recommend that once you have selected the product, that you carry out application trials on your own equipment and substrates prior to full scale production. It is not recommended that the color is accepted on our submitted panels as these are for guidance only. Some metallic coating powders can give rise to color differences on varying substrates due to the base powder not being fully opaque and therefore may not always hide blemishes on the substrate such as weld

lines etc. Other electrostatic powder application equipment may also give differing effects when compared to laboratory applied panels.

Application Plant

Automatic application equipment will give greater consistency of finish than manual hand operated guns. It is advised that all plant parameters are fully recorded for future repeatability. It is important to note all settings for KV, uA, air pressures, gun distance to object, conveyor speeds etc. It is recommended that manual touch in should be carried out prior to automatic application

A fluidized hopper will supply powder more consistently than a box feeder type system. The vibration of a box feeder may cause separation so that the heavier metallic particles may sink to the bottom of the box resulting in inconsistent effect.

Gun nozzles should be monitored and cleaned at regular intervals to prevent buildup of metallic pigment. These may require cleaning every 15 minutes for some products! Slotted nozzles may reduce the possibility of striping effects on large flat surfaces, but they should be monitored carefully for pigment build up inside the nozzle that will intermittently spit out and spoil the surface of the coated work piece.

Some experimentation may be required to find the ideal gun parameters. Our recommended starting points would be 50-70KV, with a medium of 50-60uA, and a gun to part distance of 200-250mm. If automatic current limiters are being used it may be necessary to increase gun to part distance to allow higher current for improved charging.

Some metallics may give a dry texture effect if the emitted gun voltage is less than 60KV. If this texture occurs anywhere on the coated object, increase the KV to maximum setting and if possible, check the gun for charging faults.

Powder feed rates should be kept to a minimum to give maximum opportunity for the powder to pick up the charge. Reduced atomizing air will also help prevent separation of the metallic pigment particles. It may also be necessary to reduce conveyor speeds to obtain sufficient film thickness of coating at lower powder outputs.

Always try to coat the main face of the component last to prevent any visible differences that may occur due to wrap on edges.

If manual spraying is the only available option, then it is recommended that the gun to part distance is kept constant at all times. Varying the gun to part distance will result in variation in the metallic effect. Powder with a higher metallic pigment content may cause a dry spray texture effect when applied with a manual gun. This is caused by pigment separation in the gun and feed hose when the gun trigger is released or by low KV. When the gun is triggered an initial flow of air will blow the separated pigment out of the gun causing a concentrated spray of metallic pigment on an area of the component giving rise to a texture effect. To overcome this problem, try to coat the entire article without releasing the gun trigger or when the gun is initially triggered point the gun away from the article until the powder comes out in a steady flow. The powder feed air should also be reduced which helps prevent the initial air surge from blowing any separated pigment out

of the feed hose before the main powder pickup has begun. Also set KV and uA to maximum possible setting.

Color and Effect

Film thickness needs to be controlled to maintain a consistent color and effect. Thicker films will tend to have more metallic effect. This is because the metallic particles in the powder will migrate to the surface of the coating during stoving. Therefore, the more powder applied, the more metallic pigment there is to come to the surface.

Care should also be taken when comparing finished articles or on final assembly of components. Metallic pigments can have different orientation levels during the powder curing stage. This may cause certain types of products, like coarse sparkles, to look lighter or darker when rotated through various angles! Therefore, it is important to ensure that items are placed on jigs in the same orientation prior to coating and especially important if some components require subsequent remedial overcoating.

The level of metallic effect will be affected by gun to part distance gun voltage and current. Generally, the further the gun is away from the part, the less metallic will attract to it. Too low KV and uA settings can also result in poor charge retention for the powder and can give a very high concentration of effect pigment being deposited on the workpiece resulting in a much higher than expected metallic effect.

Whenever possible the job should be completed with the same batch of powder. Metallic powder coatings may

show a slight variation between batches of the same product.

Troubleshooting

If changing the gun settings does not help overcome an application problem, then it may help to discuss the problem with the gun manufacturer. Sometimes changing the powder feed hose to a different material or internal diameter may help prevent separation. Some gun manufacturers have specific attachments for metallic powder coatings which help prevent charge backtracking.

Generally, the initial problem occurs when changing from a non-metallic to a metallic because powder flow rates and gun voltages need to be reduced. Patience is the key to successful application.

Printed Date: Jun-22

PD911278G - METALLIC BLACK GREY POLYESTER GLOSS

Attributes	
Chemical Type	
Specific Gravity (Theoretical) (kg/l)	1.48 +/-0.10
Coverage @ 1 µm DFT m ² /kg	
Technical Features	
Film Properties	Range/Value
Recommended Film Thickness	60-80 microns
Flexibility (Cylindrical Mandrel)	
Flexibility (Conical Mandrel)	
Adhesion	
Gloss (60 degrees)	Visual Only
Gloss (20 degrees)	
Direct Impact (cm/kg)	
Reverse Impact (cm/kg)	
Erichsen Cupping Test (mm)	
Cure Cycle	10 MINS @ 180C Metal Temperature
Appearance	
Application	Suitable for automatic and manual electrostatic application. Please check with your sales representative for Tribo.
Pretreatment	The surface to be coated must be free from oils, grease, and flash rust. A good quality pre-treatment process is recommended for optimum performance.
Substrate	Suitable for metal substrate.
Approval	
Version	

Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product. Environmental Data Sheet (EDS), Product (SDS) please visit your local Sherwin-Williams facility or www.PaintDocs.Com. Please direct any questions or comments to your local Sherwin-Williams facility. **Note:** All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found at www.Sherwin.Com. Please review these terms and conditions prior to the purchase of the products. Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. **SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.

Internal Use-IU-COR-00047