

# Alesta® AP

## Polyester Architectural AE Fine Texture

### AE03051101620 RAL 1016 SULFUR YELLOW

Polyester Architectural is a standard durability TGIC free and lead free polyester powder coating, especially formulated for application on aluminum extrusion and sheets, steel and galvanized steel substrates. Polyester Architectural meets the requirements of the building industry thanks to its excellent outdoor durability and mechanical properties.



#### Characteristics

- Fine Texture
- Solid
- Tribo/Corona

#### Colour Chart

- RAL 841-GL

#### Usage Area

- Aluminum profiles and sheets
- Verandas, doors, window frames, facades
- Urban furniture
- Steel or galvanized steel for cladding



#### Approvals

|           |   |
|-----------|---|
| Qualicoat | Class 1: P-0145, P-0846, P-0673, P-0800, P-1661 |
| GSB       | Florida 1: 171e                                 |
| Marine    | CE 0575, CE 2690                                |



- Product approved by QUALICOAT
- QUALICOAT is a quality label for licensed coater
- This powder coating complies with the European Directives "Restriction of the use of certain hazardous substances" 2011/65/EU and 2015/863/EU (RoHS)
- Meets the requirements of AAMA 2603-15
- Meets the requirements of EN 12206-1 (formerly BS 6496), EN 13438 (formerly BS 6497)
- Classification A2 (non flammable) of reaction to fire in accordance with NF EN 13501-1:2018



#### Special Application Advice

- This colour has limited hiding power and therefore the colour conformity of coated parts must be assessed by the coater.

The following data has been obtained under laboratory conditions as described below. Actual product properties such as gloss, colour and finish may vary depending on application conditions.



## Test Conditions

- Curing Conditions (object temperature) 7 min @ 180°C
- Substrate 0,8 mm AA5005 Aluminium panels (AA6060 or AA6063 for Acetic Salt Spray)
- Film thickness 70 ± 10 µm  
EN ISO 2360

## Physical Data

- Density 1,57 g/cm<sup>3</sup>  
calculated



## Product Performance / Film Properties


|  |   |
|--|---|
| Gloss @ 60°<br>EN ISO 2813   | 5 ± 2   |
| Impact Resistance<br>EN ISO 6272 / ASTM D2794                        | 2,5 Nm / 22 inch-pound  |
| Adhesion<br>EN ISO 2409  | GT0   |
| Buchholz Hardness<br>EN ISO 2815                                     | 80  |
| Erichsen Cupping<br>EN ISO 1520                                      | 5 mm  |
| Cylindrical Mandrel Bending<br>EN ISO 1519                           | 5 mm  |
| Mar Resistance (Martindale)<br>CEN/TS 16611 (according to Qualicoat) | Residual gloss 70-90 %  |
| Kesternich (SO <sub>2</sub> ) 30 cycles<br>EN ISO 3231               | No change   |
| Acetic Salt Spray 1000 h<br>EN ISO 9227                              | Maximum 16 mm <sup>2</sup> infiltration over a scratch length of 10 cm  |
| Resistance to Boiling Water  | No defect or peeling after 2 hours  |
| Humidity Chamber 1000 h<br>EN ISO 6270-2                             | No blistering   |
| Mortar Resistance<br>EN 12206-1                                      | No change (in accordance with Qualicoat requirements)   |
| Weathering - Florida<br>EN ISO 2810                                  | 1 year, Residual gloss ≥ 50%, Colour change ΔE: According to Qualicoat requirements, Colour Change ΔL*, ΔC*: According to GSB |
| Accelerated weathering - Xenon lamp<br>EN ISO 16474-2                | 1000 hours, Residual gloss ≥ 50%, Colour change ΔE: According to Qualicoat requirements                                       |
| Accelerated Weathering - UVB-313<br>EN ISO 16474-3                   | 300 hours, Residual gloss ≥ 50%   |



## Curing Conditions (object temperature)

Can be cured using a variety of methods, e.g. IR, convection, combi ovens. In direct gas ovens, combustion by-products may cause significant colour changes (for specific advice, please contact us).

4-20 min @ 190°C  
7-25 min @ 180°C  
12-30 min @ 170°C



## Storage Stability

24 months/35°C

Shelf life applies to materials stored in sealed plastic bags under dry and cool conditions.



## Substrate Preparation

- On aluminium, steel and hot-dip galvanized steel: both chemical pre-treatment and mechanical surface preparation are compatible with Polyester Architectural. Surface preparation should be chosen according to type of substrate and required performance.
- On steel and hot-dip galvanized steel, corrosion resistance may be further enhanced by the use of our Alesta® ZeroZinc protective primers (please contact us for further information).
- The suitability of the surface preparation should be tested by the coater beforehand using appropriate test methods. Reference should be made to guidelines issued by Qualicoat, Qualisteelcoat and GSB.



## Application

- Do not mix this product with other powder coatings.
- Substrate should be correctly cleaned before use.
- Can be applied with manual or automatic guns.
- Film thickness: application settings will depend upon the geometry of the object being coated as well as the required film thickness. It is the responsibility of the applicator to make the appropriate adjustments. Certain colours should be applied at higher film thickness to ensure full coverage and therefore colour homogeneity. Below this limit, colour variation may occur due to differences in film thickness.
- Great care is taken during our manufacturing process but small variations in colour and/or appearance are unavoidable with effect colours. Therefore we recommend that a single batch of powder coating should be used to coat parts that will be subsequently assembled together. Differences are more likely with effect powder coatings such as metallic, pearlescent, speckled, textured and combinations thereof. Differences will be more easily visible on large coated parts such as cladding panels, flat sheets etc.
- Recycling of the powder: possible up to 30 % for solid colours. For special finishes (for example metallic, pearlescent, speckled), please refer to our website and the 'Metallics are us - Tips for Users' guide.



## Comments

- Certain chemicals or domestic cleaning products may cause damage to the appearance of the coating. We recommend testing a small inconspicuous area first to confirm suitability.
- For maintenance of material coated with Polyester Architectural powder coating, it is extremely important to follow our recommendations (defined in the Alesta® AP warranty document).
- Strict implementation of the correct maintenance procedure is needed to maintain the validity of the warranty and the decorative appearance of the coating.
- Coated parts should be packed after they are fully cooled using suitable materials that are free of plasticizers. Packaged parts should be stored under cover to avoid the formation of condensation (for example under plastic wrapping film) which could result in permanent marks on the surface of the coating.



## Safety

Consult the Safety Data Sheet prior to use

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.

Copyright 2022, Axalta Coating Systems, LLC and all affiliates. The Axalta logo, Axalta™, Axalta Coating Systems™ and all products denoted with ™ or ® are trademarks or registered trademarks of Axalta Coating Systems, LLC and its affiliates. Axalta trademarks may not be used in connection with any product or service that is not an Axalta product or service.