

PRODUCT NAME

Ferrozinc

ORIGINALLY ISSUED

05/10/2017

VERSION

1.0

PRODUCT CODE

PRIFERRO

VERSION DATE

05/10/2017



PRODUCT DESCRIPTION

FERROZINC is a high performance water thinnable rust converter. It is an easily applied single pack material with excellent long term conversion properties. In many situations blast cleaning is not cost effective or practical, and though Ferrozinc is not an equivalent alternative to shot blasting, it does offer a far superior performance than conventional coatings applied to slightly rusted surfaces.

FERROZINC is used after simple wire brushing to remove surface rust. A dramatic colour change from white to black will show that the rust has been effectively neutralised.

FERROZINC should then be overcoated with a suitable primer & topcoat system for prolonged corrosion resistance.

Salt spray and extended durability testing has proven FERROZINC to out-perform competitive rust conversion materials.



IMPORTANT INSTRUCTIONS BEFORE USE

- Read and follow SDS, TDS and label instructions
- Stir all paints thoroughly before use
- Always use the same batch number on the same job
- Check colour & sheen. HMG will not accept any discrepancies arising after use
- Filter the product immediately before use
- Reduce emissions and maintain quality by replacing tin lid after use
- If in any doubt speak HMG Technical Service Department on (0161) 205 7631



MAXIMUM VOC CONTENT (RFU)

0.03Kg/L

REGULATIONS / COMPLIANCE

- Not Applicable



COLOUR RANGE

- N/A



GENERAL INFORMATION

Solids By Volume 44.00%
Coverage 20 square metres per litre @ 15 microns dft
Flashpoint X°C
Storage Store between 5°C - 25°C. When not in use, cans must be kept sealed
Shelf Life 12 months from delivery date in original sealed containers



CLEANING

Surfaces should be wire brushed to remove loose rust. Soluble salts should be removed by washing with water, as they may slow down the conversion process.

FERROZINC should not be used over oil/grease contamination, or existing paint as this will render the product ineffective.



SURFACE PREPARATION

Please refer to Knowledge Base for details on Surface Preparation.



SUITABLE SUBSTRATE & THEIR SUITABLE PREPARATION

MILD STEEL

Remove millscale and thoroughly degrease using suitable HMG Prep Clean
Abrade with P80-P180 if necessary before applying HMG Primer



ADDITIONAL INFORMATION

Use a short pile stipple brush, applying a light coat.

Scrub well into rusted areas only. Avoid coating non-rusted areas wherever possible.



HEALTH AND SAFETY

- Refer to SDS and tin label prior to use.

APPLICATION METHODS





MIXING RATIO

--	--	--	--	--	--	--	--



VISCOSITY

	RFU						
--	-----	--	--	--	--	--	--

	NUMBER OF COATS (GUIDE ONLY)			
	1 thin coat			
	FLASH OFF			
	15-30 mins			
	DRYING TIME			
	Touch dry	20-30mins @20°C		
	Hard dry	60mins @20°C		
	Full dry	2-3hrs @20°C		
	RECOATABILITY / OVERCOATING			
	after 2-3 hours			
	WET FILM THICKNESS*			
	30 microns maximum			
	DRY FILM THICKNESS*			
	15 microns maximum			
<p>* - HMG Technical Data Sheets indicate a Dry Film Thickness that will be achieved when applying a particular Wet Film Thickness. These values are a guide only and are not to be used as specifications. Film thickness will vary depending on actual use and specification. Great care should be taken to achieve the dft stated in the agreed specification and to avoid areas of excessively low or high thickness.</p>				

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is to the best of HMG's knowledge and belief accurate and reliable as of the date indicated. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability and completeness of such information for their own particular use. For professional use only.